

Function :



Intumescent materials assume two important functions in the fire door:

1. sealing of joints to avoid the escape of hot gas due to the overpressure in the furnace
2. fixation of the door blank weakened by burning to the frame

Choice and Installation :

The choice and the structure of the material with the suitable characteristics is of great importance.

Under certain circumstances intumescent materials can be fitted through frame and edges either open or covered.

			
Characteristics	Palusol	Intumex Promaseal	Interdens
Chemistry	Natrium-Silikat	Graphit	Ammonium-Phosphat
Reactions-Temperature	100°	150°	150°
Foaming-Volume	1 : 7	1 : 7 - 1 : 10	1 : 25 - 1 : 50
Pressure appox.	min. 9 bar	6 bar - 10 bar	0 bar
Direction	thickness	thickness	3-dimensional
Duration	once	permanent	permanent
Fitting	covered	open possible	open possible
Producer	BASF	INTUMEX, R. Kuhn, Promat	Dr. Wolman

Addresses:

BASF Aktiengesellschaft
67056 Ludwigshafen
ph.: +49-621/ 60-0
fax: +49-621/ 60-42525

Intumex
A-4021 Linz
ph.: +43-70/ 6912-3353
fax: +43-70/ 6912-3740

Promat GmbH
40878 Ratingen
ph.: +49-2102/ 493-0
fax: +49-2102/ 493-111

Dr. Wolman GmbH
76547 Sinzheim
ph.: +49-7221/ 800-0
fax: +49-7221/ 800-210

Rolf Kuhn GmbH
82327 Tutzing
ph.: +49-8158/ 2501-0
fax: +49-8158/ 2501-25

LORIENT Polyprod. Ltd.
UK - Newton Abbot
ph.: +44-1626/ 834 252
fax: +44-1626/ 833 166

Mann McGowan
GB - Aldershot
ph.: +44-1252/ 333 601
fax: +44-1252/ 322 724